

Melamine facing

Melamine facing

PremiumBoard Pyroex

#### November 2022

# **Technical data**

# DecoBoard Pyroex

Flame resistant particleboard with decorative melamine resin facing on both faces, awarded with the Blue Angel.

#### Applications



Furniture and interior fitting



Fire protection

### Properties



Variety of decors and / or textures



Easy care



Antimicrobial





Flame retardant



Particularly low emission

#### Certificates







Specification						Unit	Test standard
Nominal thickness	10	13	16	18	19	mm	
Tolerance on thickness	±0.3 for class 1, 2 +0.5/-0.3 for class 3A, 3B, 4 and gloss surfaces				mm	EN 14323	
ength- and width tolerance	±5				mm	EN 14323	
Length- and width tolerance (precut panels)	± 2.5				mm	EN 14323	
Flatness	$\leq 2^{1}$ $\leq 2^{1}$ $\leq 2^{1}$				mm/m	EN 14323	
Edge damage	≤ 10					mm	EN 14323
dge damage (pre-cut panels)	≤3					mm	EN 14323
Surface defects (Points)	≤2				mm²/m²	EN 14323	
Surface defects (Defect in the ength)	≤ 20				mm/m²	EN 14323	
Resistance to scratching	≥ 1.5 <sup>2)</sup>				N	EN 14323	
Resistance to staining	≥ 3				Rating	EN 14323	
Resistance to cracking	≥3				Rating	EN 14323	
Resistance to abrasion (plain colours)	3A				Class	EN 14323	
Resistance to abrasion (printed designs)	1				Class	EN 14323	
Resistance to colour change in kenon arc light	min. 4 Grey Scale Grade					EN 14323	
Mean density	720 - 640 <sup>3)</sup>	720 - 640 <sup>3)</sup>	640 - 620 <sup>3)</sup>	640 - 620 <sup>3)</sup>	640 - 620 <sup>3)</sup>	kg/m³	EN 323
Bending strength	11 <sup>3)</sup>				N/mm²	EN 310	
Bending modulus of elasticity	1,800 <sup>3)</sup>	1,800 <sup>3)</sup>	1,600 <sup>3)</sup>	1,600 <sup>3)</sup>	1,600 <sup>3)</sup>	N/mm²	EN 310
nternal bond	0.4 3)	0.4 <sup>3)</sup>	0.35 <sup>3)</sup>	0.35 <sup>3)</sup>	0.35 <sup>3)</sup>	N/mm²	EN 319



November 2022

# **Technical data**

## **DecoBoard Pyroex**

Specification						Unit	Test standard
Nominal thickness	10	13	16	18	19	mm	
Surface soundness	0.8 3)				N/mm²	EN 311	
Formaldehyde release	E1 E05						
Reaction to fire (Euroclass)	B-s1,d0 <sup>4)</sup>					EN 13501-1	
Reaction to fire	flame retardant						

<sup>1)</sup> If symmetrical construction

Specification					Unit	Test standard
Nominal thickness	22	25	28	38	mm	
Tolerance on thickness	±0,5					EN 14323
Length- and width tolerance	±5					EN 14323
Length- and width tolerance (precut panels)	± 2.5					EN 14323
Flatness	≤ 2 <sup>1)</sup>					EN 14323
Edge damage	≤ 10					EN 14323
Edge damage (pre-cut panels)	≤3					EN 14323
Surface defects (Points)	≤2					EN 14323
Surface defects (Defect in the length)	≤ 20					EN 14323
Resistance to scratching	≥ 1.5 <sup>2)</sup>					EN 14323
Resistance to staining	≥3				Rating	EN 14323
Resistance to cracking	≥3					EN 14323
Resistance to abrasion (plain colours)	3A					EN 14323
Resistance to abrasion (printed designs)	1				Class	EN 14323
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade					EN 14323
Mean density	620 - 600 <sup>3)</sup>	620 - 600 <sup>3)</sup>	600 - 580 <sup>3)</sup>	580 - 540 <sup>3)</sup>	kg/m³	EN 323
Bending strength	10.5 <sup>3)</sup>	10.5 <sup>3)</sup>	10.5 <sup>3)</sup>	8.5 <sup>3)</sup>	N/mm²	EN 310
Bending modulus of elasticity	1,500 <sup>3)</sup>	1,500 <sup>3)</sup>	1,500 <sup>3)</sup>	1,200 <sup>3)</sup>	N/mm²	EN 310
Internal bond	0.3 <sup>3)</sup>	0.3 <sup>3)</sup>	0.3 <sup>3)</sup>	0.2 <sup>3)</sup>	N/mm²	EN 319
Surface soundness	0.8 3)					EN 311
Formaldehyde release	E1 E05					
Reaction to fire (Euroclass)	B-s1,d0 <sup>4)</sup>					EN 13501-1
Reaction to fire	flame retardant					

<sup>1)</sup> If symmetrical construction

<sup>2)</sup> Except smooth and matt structures, as well as decors with mother-of-pearl effect

<sup>3)</sup> Core material

<sup>4)</sup> DecoBoard Pyroex fulfills the additional specifications 'lowest smoke emission' and 'no burning droplets' and thus the highest building authority requirements for flame-retardant building materials according to EN 13501-1.

<sup>&</sup>lt;sup>2)</sup> Except smooth and matt structures, as well as decors with mother-of-pearl effect

<sup>3)</sup> Core material

<sup>4)</sup> DecoBoard Pyroex fulfills the additional specifications 'lowest smoke emission' and 'no burning droplets' and thus the highest building authority requirements for flame-retardant building materials according to EN 13501-1.



November 2022

### **Technical data**

## DecoBoard Pyroex

#### Additional information

Product standard	• EN 14322
Areas of application	<ul> <li>Preventive fire protection in the decorative sector. For interior fitting as wall and ceiling coverings, installations, room dividers and furniture, in industrial and administrative buildings, schools, sports and festival halls, hotels and care facilities.</li> </ul>
Core material	<ul> <li>PremiumBoard Pyroex</li> <li>Flame resistant particleboard, suitable for non load-bearing purposes in dry areas, for interior fitting and for furniture subject to higher demands on fire protection.</li> </ul>
Product safety	<ul> <li>This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered.</li> <li>The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011.</li> <li>We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.</li> </ul>
Antimicrobial effect	Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Resistance to heat	<ul> <li>Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.</li> </ul>
Special	<ul> <li>A protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation).</li> </ul>
Note	FSC certification or PEFC certification available on request.  FSC license code: FSC® C011773  PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul> <li>Decor, structure and core board all influence the final appearance of the end product.</li> <li>Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect.</li> <li>The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors.</li> <li>To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.</li> </ul>

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

### © Copyright 2022 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.