

November 2022

Technical data

DecoBoard Real Metal P2

Urea resin bonded particleboard with real aluminium foil on both sides in direct facing method.

Applications

Furniture and interior fit-

Properties



Certificates









Specification				Unit	Test standard
Nominal thickness	16	18	19	mm	
Tolerance on thickness	±0.3 for class 1, 2 +0.5/-0.3 for class 3A, 3B, 4 and gloss surfaces			mm	EN 14323
Length- and width tolerance	± 5			mm	EN 14323
Flatness	≤ 2 ¹⁾		mm/m	EN 14323	
Edge damage	≤ 10		mm	EN 14323	
Surface defects (Points)	≤2			mm²/m²	EN 14323
Surface defects (Defect in the ength)	≤ 20			mm/m²	EN 14323
Resistance to scratching	≤1			N	EN 14323
Resistance to staining	min. 3		Rating	EN 14323	
Resistance to cracking	≥3		Rating	EN 14323	
Resistance to colour change in kenon arc light	min. 4 Grey Scale Grade			EN 14323	
Mean density	640 - 620 ²⁾		kg/m³	EN 323	
Bending strength	11 ²⁾			N/mm²	EN 310
Bending modulus of elasticity	1,600 ²⁾			N/mm²	EN 310
Internal bond	0.35 ²⁾			N/mm²	EN 319
Surface soundness	0.8 ²⁾		N/mm²	EN 311	
Formaldehyde release		E1 E05			
Reaction to fire (Euroclass)	D-s2,d0 according to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m³)				

¹⁾ If symmetrical construction

²⁾ Core material



November 2022

Technical data

DecoBoard Real Metal P2

Additional information

Areas of application	 Exclusively for vertical applications in high-quality interior fitting, shop fitting and trade fair construction, for kitchen and residential furniture. Real aluminium surfaces are not suitable for horizontal surfaces and/or surfaces exposed to mechanical loads.
Core material	 ClassicBoard P2 Urea resin-bonded particleboard, type P2 in accordance with EN 312, suitable for non load-bearing purposes in dry areas.
Product safety	 This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.
Resistance to heat	 Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.
Special	 The real metal surface is made of aluminium. Unlike classic, melamine-impregnated decor papers, real metal surfaces may provide certain visual effects on the surface. Differences in colour, a slight unevenness in the surface and small indentations may also occur. These are not quality defects, but proof of the real metal surface, distinguishing it from imitations. Please consider that metal surfaces react more sensitive to scratch, impact and abrasion purposes than melamine surfaces. Also the chemical resistance is comparatively lower. Cut to size is not available. A protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation). Please note the visible longitudinal joint of the real metal foil (2 strips) at approx. 1,380 mm and the effective length of min. 2,780 mm. Decors: M80000 Alu 1, Stainless Steel Effect / M80001 Alu 2, Nickel Effect
Note	 FSC certification or PEFC certification available on request. FSC license code: FSC[®] C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2022 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com